

BEYOND FLOORS...

URECO GTC-OP

100% SOLID EPOXY TOP COAT ORANGE PEEL
ULTRA GLOSS FINISH
TDSGTC-OPEN.V03

PRODUCT DESCRIPTION

URECO GTC-OP is a two-component, 100% solids epoxy protective coating system offering a textured, seamless orange peel finish. URECO GTC is also solvent free and self-priming. The application of two coats is recommended. URECO GTC-OP.

BENEFITS

- Odorless
- Easy application
- Durable, impermeable, seamless and esthetic
- Superior Adhesion
- Good chemical and mechanical resistance
- Does not support growth of bacteria and fungus
- Easily cleaned, maintained and a more sanitary work environment
- Meets Canadian Food Inspection Agency

COLORS

SOLID COLORS

White, Very Light Gray, Light Gray, Steel Gray, Telegrey, Agate Gray, Azure, Deep Blue, Lime Green, Pine Green, Desert Tan, Tile Red, Black, Safety Yellow and Safety Red

TYPICAL USES

- Pharmaceutical
- Industrial
- Automotive Service Bays
- Institutional Buildings
- Commercial Buildings
- Hospital
- Residential
- Aerospace
- Plant Vehicle Aisles
- Showrooms, shops, dealerships
- Bars, banquet hall
- Hotels, lobbies, kitchens and restaurants
- Shopping centers, retail stores
- Spa, solariums, salons
- Casinos
- Airports, railway stations

SURFACE PREPARATION

Surface preparation is required. Substrate must be profiled, dry, clean, oil free, and sound. Use Ureco Degreaser to remove all contaminants (oils, greases and others). Remove any dust, laitance, dirt, curing agent impregnations, wax, foreign matter, coatings and others from the surface by an appropriate mechanical to achieve a profile equivalent to ICRI CSP 2-3 with Blastrac and/or diamond grinder with dust free collector. Need proper bonding to the substrate. Call the Technical Department for preparation recommendation.

TECHNICAL INFORMATION

Solid Colors	15 colors
Cure Time @ 21°C	
Recoat	8-12 hours
Foot traffic	12-24 hours
Light wheel traffic	24 hours
Full service	48 hours
Full cure	7 days
Mix Ratio (by volume)	2 component kit 2 Part A (resin) 1 Part B (hardener)
Coverage	1 st coat: 6-8 mils (200-260 sqft/gal) 2 nd coat: 12-16 mils (100-135 sqft/gal)
Pot Life @ 25°C	25-30 minutes
Solid by weight	100
VOC Content	< 30g/L
Toxicity	Non-toxic Low odor No ventilation required

PHYSICAL PROPERTY

TEST METHOD

RESULT

Adhesion to concrete CS17 / 1000 Cycles / 1000g	> 300 psi (substrate failure)	
Bond Strength Coefficient of Friction Standard Slip	ASTM D-2047	0.9 0.7
Resistant Smooth		
Flexural Strength	ASTM D-638	5 500psi
Hardness (Shore D)	ASTM D-2240	70-80
Tensile Strength	ASTM D-638	1000-1500, psi
Water Absorption	ASTM D-570	0.30%

- Pot life is shorter at higher temperature.
- Before using any URECO product, be sure the Safety Data Sheet (SDS) is read and understood.

POWERBLAST CANADA

379 rue de l'Aigle, Saint-Eustache, Quebec, Canada, J7R 0M9
1-866-975-1133
www.powerblastcanada.com

LIKE & FOLLOW US ON SOCIAL MEDIA!



Facebook.com/powerblastcanada



Linkedin/powerblastcanada



Instagram.com/urecoflooring

BEYOND FLOORS...

PACKAGING

URECO GTC is available in 3 gallons / kit or 15 gallons / kit (pails). All kits containing 2 part A of resin and 1 part B hardener.

PRIMING

Self-primer

MIXING

CLEAR AND COLORED VERSION

Pre-mix each component separately. Empty 1 part of component B with two parts component A, (mixing ratio 2 for 1) into an appropriate mixing container. Mix the combined components for at least 2-3 minutes using a low-speed drill (300-450 rpm) to minimize entrapping air in the system. When completely mixed, the product should be uniform in color and consistency.

APPLICATION

URECO GTC-OP is applied in two steps:

1. Apply one coat of solid color Ureco GTC-OP. The coating must be dry to the touch before applying the second coat.
2. Spread the product evenly using a squeegee and level with an appropriate textured roller to create an orange peel texture. Pull towards you to obtain the required thickness and an even surface. Perform the perimeters using a brush beforehand. To be applied by certified applicators.

NOTE: Do not exceed 24 hours between coats. If this time is exceeded, sanding of the surface is required to ensure bonding.

CLEANING

This product is considered to be a low maintenance flooring solution; however, certain textures and service environments do require certain procedures. Please refer to the "Maintenance Recommendation".

STORAGE CONDITIONS

URECO GTC-OP must be stored in a dry cool place between 15°C and 21°C. Do not allow to freeze. The shelf life of this product is 12 months from ship date in the original unopened container. Do not store near open flame.

CHEMICAL RESISTANCE

This product is resistant to many common chemicals. Please call the Technical Department for actual resistance to specific chemical/agents.

MOISTURE CONCERNS

Moisture vapor transmission in the slab should be measured prior to application of polymeric systems to ensure a long lasting, durable installation.

LIMITATIONS

This product is best suited for application in temperatures between 15°C and 25°C. Substrate must be clean, sound and dry. Substrate temperature must be 3°C (5.5F) above measured dew point. Moisture content of the substrate must less than 4% when coating is applied. Do not apply to surfaces where moisture vapor can condense and freeze or to porous surfaces where moisture vapor transmission will occur during the application. Do not apply in areas where the humidity is greater than 85%. Freshly applied material should be protected from dampness, condensation and water for at least 24 hours. Compressive of the concrete should be at least 25 mpa (3625) psi at 28 days. If you have any questions, please contact the PowerBlast Canada Technical Services at 1-866-975-1133

CAUTION

Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, organic vapor respirators. Follow the Safety Data Sheet (SDS) for proper personal protective equipment to use when handling this product. Use only as directed.

KEEP OUT OF REACH OF CHILDREN.

IMPORTANT NOTICE- All statements, recommendations and technical information contained in this document are based on tests and information, which PowerBlast Canada believes to be accurate as of this date. The buyer should test this product before use. PowerBlast Canada assumes no obligation or liability for results obtained from the use of this product. The product and information herein are furnished at the buyers request and risk. PowerBlast Canada will not be liable for any direct, indirect, consequential, economic or any other damage whatsoever except to replace the product and or refund the purchase price to the purchaser.

POWERBLAST CANADA


379 rue de l'Aigle, Saint-Eustache, Quebec, Canada, J7R 0M9


1-866-975-1133

www.powerblastcanada.com

LIKE & FOLLOW US ON SOCIAL MEDIA!

 Facebook.com/powerblastcanada

 Linkedin/powerblastcanada

 Instagram.com/urecoflooring